U.S. DEPARTMENT OF LABOR
Occupational Safety and Health Administration

Form Approved OMB No. 44-R1387

MATERIAL SAFETY DATA SHEET

Required under USDL Safety and Health Regulations for Ship Repairing, Shipbuilding, and Shipbreaking (29 CFR 1915, 1916, 1917)

MANUFACTURER'S NAME Dexter Corporation, Hysol Division Dexter Corporation, Hysol Division Dexter Corporation, Hysol Division Dexter Corporation, Hysol Division A15/687-4201 A580 Willow Pass Road (P.O. Box 312), Pittsburg, California 94565 CHEMICAL HAME AND SYNONYMS CHEMICAL FAMILY Modified Epoxy SECTION II - HAZARDOUS INGREDIENTS PAINT:, PRESERVATIVES, & SOLVENTS VILVIAITY PROMENT: CATALYST VEHICLE Epoxy Resins 57 METALLIC COATINGS ALLOYS WETALLIC COATINGS SOLVENTS Glass Fibers 9 FILLER METAL FILLER METAL ALLOYS ADDITIVES OTHERS OTHERS OTHERS OTHERS OTHERS None of the constituents are on OSHA's 29 CFR 1910 subpart Z Toxic and Hazardous Substance List. SECTION III - PHYSICAL DATA BCILING POINT (%F.) Decomposes before boiling SPECIFIC GRAYITY (H-20-1) Vy. POR PRESSURE (mm Hg.) Not Available PROMENT: SECTION IV - FIRE AND EXPLOSION HAZARD DATA FLASH POINT (Method used) > 200°F TCC FLASH POINT (Method used) PLASH POINT (Method used) > 200°F TCC FLASH POINT (Method used)									
Dexter Corporation, Hysol Division ADJRESS (Number, Street, City, State, and ZIP Code) ZBSO WILLOW Pass Road (P.O. Box 312), Pittsburg, California 94565 CHEMICAL NAME AND SYNONYMS SECTION II - HAZARDOUS INGREDIENTS PAINT:, PRESERVATIVES, & SOLVENTS									
THE PRINT (MEDICAL NAME AND SYNONYMS THE PRESERVATIVES, & SOLVENTS PIGMENT: PAINT:, PRESERVATIVES, & SOLVENTS PIGMENT: CATALYST VEHICLE Epoxy Resins 57 METALLIC COATINGS VEHICLE Epoxy Resins 57 METALLIC COATINGS SOLVENTS Glass Fibers 9 FILLER METAL ALLOYS OTHERS FILLER METAL ADDITIVES OTHERS FILLER METAL OTHERS FILLER METAL ADDITIVES OTHERS FILLER METAL FILLER METAL FILLER METAL TOXIC and Hazardous MIXTURES OF OTHER LIQUIDS, SOLIDS, OR GASES NONE of the constituents are on OSHA's 29 CFR 1910 subpart Z Toxic and Hazardous Substance List. SECTION III - PHYSICAL DATA BCILING POINT (°F.) Decomposes before boiling SPECIFIC GRAYITY (H20=1) V/ POR PRESSURE (mm H9.) Not Available PERCENT, VOLATILE BY VOLUME (%) SOLUBILITY IN WATER Neg. APPEARANCE AND ODOR VISCOUS GREY PASTE with Slight odor. FLAMMABLE LIMITS Lei	o. 								
THADE NAME AND SYNONYMS CHEMICAL NAME AND SYNONYMS SECTION II - HAZARDOUS INGREDIENTS PAINT: PRESERVATIVES, & SOLVENTS									
SECTION II - HAZARDOUS INGREDIENTS **AINT:, PRESERVATIVES, & SOLVENTS									
PIGMENT: RALLOYS PIGMENT: BASE METAL ALLOYS VEHICLE EDOXY Resins 57 METALLIC COATINGS SOLVENTS Glass Fibers 9 FILLER METAL ADDITIVES 5 OTHERS OTHERS Fillers 30 HAZARDOUS MIXTURES OF OTHER LIQUIDS, SOLIDS, OR GASES None of the constituents are on OSHA's 29 CFR 1910 subpart Z Toxic and Hazardous Substance List. SECTION III - PHYSICAL DATA BCILING POINT (°F.) Decomposes before boiling SPECIFIC GRAYITY (H20=1) VA POR PRESSURE (mm H9.) Not Available PERCENT, VOLLATILE BY VOLUME (%) VA POR DENSITY (AIR=1) Not Available PERCENT, VOLLATILE BY VOLUME (%) SOLUBILITY IN WATER Neg. APPEARANCE AND ODOR VISCOUS GREY PASTE with Slight odor. SECTION IV - FIRE AND EXPLOSION HAZARD DATA	CHEMICAL FAMILY Modified Epoxy FORMULA								
PIGMENT: CATALYST VEHICLE EDOXY RESIDS SOLVENTS Glass Fibers ADDITIVES OTHERS Fillers ADDITIVES OTHERS Fillers ADDITIVES OTHERS Fillers ADDITIVES OTHERS Fillers OTHERS Fillers ADDITIVES OTHERS Fillers ADDITIVES OTHERS Fillers ADDITIVES OTHERS Fillers ADDITIVES OTHERS FILLER METAL PLUS COATING OR CORE FLUX OTHERS OTHERS OTHERS FILLER METAL PLUS COATING OR CORE FLUX OTHERS OTHERS OTHERS FILLER METAL PLUS COATING OR CORE FLUX OTHERS OTHERS OTHERS FILLER METAL PLUS COATING OR CORE FLUX OTHERS OTHERS FILLER METAL PLUS COATING OR CORE FLUX OTHERS OTHERS FILLER METAL PLUS COATING OR CORE FLUX OTHERS OTHERS FILLER METAL PLUS COATING OR CORE FLUX OTHERS OTHERS FILLER METAL PLUS COATING OR CORE FLUX OTHERS FEASH POINT (Male Lambert of Coating or Core Flux OTHERS FILLER METAL PLUS COATING OR CORE FLUX OTHERS FILLER METAL PLUS COATING OR CORE FLUX OTHERS FILLER METAL PLUS COATING OR CORE FLUX OTHERS FEASH POINT (Method Method Metho									
PIGMENT: CATALYST VEHICLE EDOXY Resins 57 METALLIC COATINGS SOLVENTS Glass Fibers 9 FILLER METAL PLUS COATING OR CORE FLUX OTHERS OTHERS THAZARDOUS MIXTURES OF OTHER LIQUIDS, SOLIDS, OR GASES None of the constituents are on OSHA's 29 CFR 1910 subpart Z Toxic and Hazardous Substance List. SECTION III - PHYSICAL DATA BCILING POINT (°F.) Decomposes before boiling PERCENT, VOLATILE PROCENT, VOLATILE PERCENT, VOLATILE PROCENT, VOLATILE PROCENTY (AIR-1) Not Available ("") SOLUBILITY IN WATER Neg. APPEARANCE AND ODOR Viscous grey paste with slight odor. SECTION IV - FIRE AND EXPLOSION HAZARD DATA	ж.	TLV (Units)							
VEHICLE EPOXY Resins 57 METALLIC COATINGS SOLVENTS Glass Fibers 9 FILLER METAL PLUS COATING OR CORE FLUX ADDITIVES 5 OTHERS OTHERS THAZARDOUS MIXTURES OF OTHER LIQUIDS, SOLIDS, OR GASES 7 None of the constituents are on OSHA's 29 CFR 1910 subpart Z Toxic and Hazardous Substance List. SECTION III - PHYSICAL DATA BCILING POINT (°F.) Decomposes before boiling SPECIFIC GRAYITY (H20=1) VAPOR PRESSURE (mm H9.) Not Available BY VOLUME (%) VAPOR DENSITY (AIR-1) Not Available EVAPORATION RATE (=1) SOLUBILITY IN WATER Neg. APPEARANCE AND ODOR VISCOUS grey paste with slight odor. SECTION IV - FIRE AND EXPLOSION HAZARD DATA									
SOLVENTS Glass Fibers 9 FILLER METAL ADDITIVES 5 OTHERS OTHERS FillerS 30 HAZARDOUS MIXTURES OF OTHER LIQUIDS, SOLIDS, OR GASES None of the constituents are on OSHA's 29 CFR-1910 subpart Z Toxic and Hazardous Substance List. SECTION III - PHYSICAL DATA BCILING POINT (°F.) Decomposes before boiling SPECIFIC GRAVITY (H20=1) VA.POR PRESSURE (mm H9.) Not Available BY VOLUME (%) VA.POR DENSITY (AIR=1) Not Available EVAPORATION RATE (VAPORATION RATE (VAPORATI									
SOLVENTS Glass Fibers 9 FILLER METAL ADDITIVES 5 OTHERS OTHERS FillerS 30 HAZARDOUS MIXTURES OF OTHER LIQUIDS, SOLIDS, OR GASES 7 None of the constituents are on OSHA's 29 CFR 1910 subpart Z Toxic and Hazardous Substance List. SECTION III - PHYSICAL DATA BCILING POINT (°F.) Decomposes before boiling SPECIFIC GRAVITY (H20=1) V4 POR PRESSURE (mm H9.) Not Available BY VOLUME (%) V4 POR DENSITY (AIR=1) Not Available (CPAPORATION RATE (PAPORATION RATE (PAPORA									
ADDITIVES OTHERS FillerS HAZARDOUS MIXTURES OF OTHER LIQUIDS, SOLIDS, OR GASES None of the constituents are on OSHA's 29 CFR-1910 subpart Z Toxic and Hazardous Substance List. SECTION III - PHYSICAL DATA BCILING POINT (°F.) Decomposes before boiling SPECIFIC GRAYITY (H20=1) VA POR PRESSURE (mm H9.) Not Available PROPER (mm H9.) Not Available ("EVAPORATION RATE ("E									
None of the constituents are on OSHA's 29 CFR 1910 subpart Z Toxic and Hazardous Substance List. SECTION III - PHYSICAL DATA BCILING POINT (°F.) Decomposes before boiling SPECIFIC GRAYITY (H20=1) V. POR PRESSURE (mm H9.) Not Available BY VOLUME (%) V. POR DENSITY (AIR=1) Not Available SOLUBILITY IN WATER Neg. APPEARANCE AND ODOR Viscous grey paste with slight odor. SECTION IV - FIRE AND EXPLOSION HAZARD DATA									
None of the constituents are on OSHA's 29 CFR-1910 subpart Z Toxic and Hazardous Substance List. SECTION III - PHYSICAL DATA BCILING POINT (°F.) Decomposes before boiling SPECIFIC GRAYITY (H20=1) VA POR PRESSURE (mm H0.) Not Available BY VOLUME (%) VA POR DENSITY (AIR=1) Not Available (CAPPORATION RATE (CAPPORAT		TLV							
SECTION III - PHYSICAL DATA BCILING POINT (°F.) Decomposes before boiling SPECIFIC GRAYITY (H20=1) V. POR PRÉSSURE (mm Hg.) Not Available BY VOLUME (%) V. POR DENSITY (AIR=1) Not Available EVAPORATION RATE (
SECTION III - PHYSICAL DATA BCILING POINT (°F.) Decomposes before boiling SPECIFIC GRAYITY (H2O=1) VAPOR PRESSURE (mm Hg.) Not Available BY VOLUME (%) VAPOR DENSITY (AIR=1) Not Available EVAPORATION RATE (
SECTION III - PHYSICAL DATA BCILING POINT (°F.) Decomposes before boiling									
BCILING POINT (°F.) Decomposes before boiling SPECIFIC GRAYITY (H2O=1) VAPOR PRESSURE (mm Hg.) Not Available BY VOLUME (%) VAPOR DENSITY (AIR=1) Not Available EVAPORATION RATE (
BCILING POINT (°F.) Decomposes before boiling SPECIFIC GRAYITY (H2O=1) VAPOR PRESSURE (mm Hg.) Not Available BY VOLUME (%) VAPOR DENSITY (AIR=1) Not Available EVAPORATION RATE (
BCILING POINT (°F.) Decomposes before boiling SPECIFIC GRAYITY (H2O=1) V**POR PRESSURE (mm H9.) Not Available By Volume (%) V**POR DENSITY (AIR=1) Not Available EVAPORATION RATE (,	1 1							
V/ POR PRESSURE (mm Hg.) V/ POR DENSITY (AIR=1) Not Available PERCENT, VOLATILE BY VOLUME (%) V/ POR DENSITY (AIR=1) Not Available EVAPORATION RATE (1.55							
V/ POR DENSITY (AIR=1) Not Available EVAPORATION RATE (becomposes before botting								
Not Available (BY VOLUME (%)								
APPEARANCE AND ODOR Viscous grey paste with slight odor. SECTION IV - FIRE AND EXPLOSION HAZARD DATA FLASH POINT (Method used) FLASH POINT (Method used)		N.A.							
SECTION IV - FIRE AND EXPLOSION HAZARD DATA FLASH POINT (Method used) FLAMMABLE LIMITS Lei	SOLUBILITY IN WATER Neg.								
FLASH POINT (Method used) FLAMMABLE LIMITS Lei									
FLASH POINT (Method Used)									
		Uel							
EXTINGUISHING MEDIA Chemical foam, dry chemicals, CO2									
SPECIAL FIRE FIGHTING PROCEDURES									
unusual fire and explosion Hazards Dense smoke may be liberated									

·								
SECTION V - HEALTH HAZARD DATA								
Rat Oral LD50 >2.0 gm/kg, estimated. Rabbit Percut LD50 >2.0 mg/kg, estimated.								
WARNING! May cause eye irritation, skin sensitization or other allergic responses.								
1								
EMERGENCY AND FIRST AID PROCEDURES Wash skin immediately with soap and water. Flush eyes immediately with plenty of								
water.		.		· · · · · · · · · · · · · · · · · · ·				
SECTION VI - REACTIVITY DATA								
STABILITY	UNSTABLE	Х	CONDITIONS	TO AVOID	nded storage conditions			
	STABLE		See Section IX					
INCOMPATABILITY (Materials to avoid)								
HAZARDOUS DECOMPOSITION PRODUCTS Compounds of carbon and nitrogen								
HAZARDOUS	MAY OCCUP	<u> </u>	Х	conditions to A Exothermic	reaction - avoid heating			
POLYMERIZATION	WILL NOT O	WILL NOT OCCUR large masses too high in temperature						
					•			
COLL COLL AN ADOCEDURES								
SECTION VII - SPILL OR LEAK PROCEDURES								
STEP: TO BE TAKEN IN CASE MATERIAL IS RELEASED OR SPILLED Remove excess. Clean with solvents.								
WASTE DISPOSAL METHOD Land burial or incineration as regulated by all governing								
agencies.	¥							
SECTION VIII - SPECIAL PROTECTION INFORMATION								
RESP. RATORY PRO	TECTION (Specify t							
VEN ILATION	LOCAL EXHAUST		ommanded		SPECIAL			
VER IEATION	Recommended MECHANICAL (General) Recommended				OTHER			
PROTECTIVE GLO	VES Dubling	кес	Johnnende		Safety glasses or goggles			
Rubber Safety grasses or goggres								
		Ų						
		SECTION	IX - SPE	CIAL PRECAU	TIONS			
PRECAUTIONS TO BE TAKEN IN HANDLING AND STORING Follow recommended storage conditions:								

Form OSHA-20 Rev. May 72

ANSI Classification 4

3 months at 77°F; 1 year at 40°F; 2 years at 0°F.